

7012C09553 HS LIR Chromate Free Epoxy Primer

Product Description

7012C09553 is a two component, chromate and lead free epoxy, corrosion inhibiting primer. 7012C09553 is suitable for use on fibre reinforced composite materials, suitable pretreated aluminium substrates, titanium and corrosion resistant steels.

- High solid, low VOC
- Low infra red quality (LIR)
- Excellent fluid resistance & adhesion characteristics
- Compatible with polyurethane topcoats

Components



Mix Ratio (by volume)

- 7012C09553 (Base) 3 parts
- 7012B (Activator) 1 part

Specifications



7012C09553 is approved to:

- SP-J-513-A-0013 Type II Class B

Product Compatibility

7012C09553 is listed on the following specifications:

- SP-J-513-A-0014
- SP-J-513-B-0307
- SP-J-513-B-0378
- SP-J-513-C-0083
- SP-J-513-M-0024

Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.

7012C09553 HS LIR Chromate Free Epoxy Primer

Surface Preparation and Pretreatment



Ensure surface to be painted is clean, dry and intact, if necessary use a high performance solvent cleaner e.g. DeSoto® CN20 or Desoclean™ 45 solvent cleaner. When required, lightly abrade using P240-P320 sand paper (mechanical sander) or P400 (hand abrade). Remove abrasive residue/dust using tack cloth, then solvent degrease.

Instructions for Use



Base may require mechanical agitation. Ensure all components are adequately dispersed. Before adding the activator to the base, thoroughly stir or shake the base component until a smooth uniform mix is obtained. Immediately after adding the activator to the base, stir thoroughly until uniform.

Note: All products and components should be placed in ambient conditions of 15-30°C (59-86°F) for at least 24 hours prior to mixing and application.



Induction Time:


Not required



Viscosity: (23°C/73°F)

- AFNOR4 24 - 26 seconds
- BSB3 46 - 50 seconds
- FORD4 21 - 23 seconds
- ISO4 43 - 48 seconds
- ZAHN2 28 - 30 seconds

Note: Viscosities quoted are typical ranges obtained when using specified mix ratio.



Pot Life:

4 hours @ 21 - 25°C (70 - 77°F)

Application Guidelines

Recommended Application Conditions:

Temperature 15 - 35°C (59 - 95°F)
Relative Humidity 30 - 85%

Application:

Apply a single coat to achieve a dry film thickness between 20 - 30 µm


7012C09553 HS LIR Chromate Free Epoxy Primer



Theoretical Coverage: (ready for use)
24 m²/Lt @ 25 µm dry film thickness
960 ft²/US gal @ 1 mil dry film thickness

Recommended Dry Film Thickness:

20 - 30 µm
0.8 - 1.2 mil



Dry Film Density:

1.72 g/cm³
14.3 lbs/US gal

Dry Film Weight:

43 g/m² @ 25 µm dry film thickness
0.0088 lbs/ft² @ 1 mil dry film thickness

Note: These application guidelines represent PPG's best advice for usage in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.

Equipment: 7012C09553 is compatible with all current forms of current spray equipment.



Equipment Type	Tip Size	Pressure
Airmix	11"	Refer to Manufacturer
HVLP Air Spray	1.3 to 1.8mm	29 to 43 psi (2 to 3 bar)
Pressure Pot	1.0 to 1.2mm	29 to 43 psi (2 to 3 bar)
Airless	11"	Refer to Manufacturer
Air-assisted Airless Electrostatic	11"	Refer to Manufacturer
Low Pressure Electrostatic	1.0 to 1.2mm	72 to 97 psi (5 to 6 bar)

Equipment Cleaning:

Clean spray equipment before use and as soon as possible after use, DeSoto® CN20, CN44 or Desoclean™ 45 solvent cleaners are recommended.

7012C09553 HS LIR Chromate Free Epoxy Primer

Physical Properties

**Colour:**

Black


**Gloss:**

<20 units with a 60° gloss meter



Drying Times	23°C (73°F)	40°C (104°F)	70°C (158°F)	125°C (257°F)
Dry to Handle	8 hours	2 hours	45 minutes	20 minutes
Dry to Tape	8 hours	2 hours	45 minutes	20 minutes
Hard Dry	16 hours	4 hours	90 minutes	30 minutes
Re-coat with Self	30 to 45 minutes	When Cool	When Cool	When Cool
Dry to Overcoat	4 hours (min.) 72 hours (max.)	45 minutes	45 minutes	20 minutes
Full Cure	7 days	3 hours	3 hours	1 hour

Note: Drying times listed above are dependent upon film thickness applied, air flow conditions and application technique.

**Flash Off:**

15 - 30 minutes before force drying.

**VOC: (ASTM)**

Mixed ready for use	<350 g/Lt
7012C09553 Base Component	335 g/Lt
7012B Activator	365 g/Lt

**Flash Point:**

7012C09553 Base Component	<21°C (70°F)
7012B Activator	25°C (77°F)

Shelf Life:

7012C09553 Base Component	24 months in original unopened container
CA7012B Activator	24 months in original unopened container

Note: Shelf life may vary due to OEM specification requirements. Refer to container label for specific shelf life information.

7012C09553 HS LIR Chromate Free Epoxy Primer

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

Note: When procuring to a qualified material specification, follow those storage instructions.

7012C09553 HS LIR Chromate Free Epoxy Primer

Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

Additional information can be found at: www.ppgaerospace.com

For sales and ordering information call the local PPG office at the numbers listed below:

Asia Pacific

ASC – Australia

Tel 61 (3) 9335 1557
Fax 61 (3) 9335 3490

ASC – Japan

Tel 81 561 35 5200
Fax 81 561 35 5201

ASC – South East Asia

Tel 65 6861 1119
Fax 65 6861 6162

ASC – Suzhou

Tel (86-512) 6661 5858
Fax (86-512) 6661 6868

ASC – Tianjin

Tel (86-022) 2482 8625
Fax (86-022) 2482 8600

Europe and Middle East

ASC – Central Europe

Tel 49 (40) 742 193 10
Fax 49 (40) 742 139 69

ASC – Middle East & India

Tel (971) 4 883 9666
Fax (971) 4 883 9665

ASC – North Europe

Tel 44 (0) 1388 770222
Fax 44 (0) 1388 770288

ASC - South Europe

Tel 33 (0) 235 53 43 71
Fax 33 (0) 235 53 54 44

Americas

1 (818) 362-6711 or 1-800-AEROMIX

Desoclean and DeSoto are trademarks of PRC-DeSoto International, Inc.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

This document has been reviewed by the PPG Aerospace Export Control Department and has been determined to contain only EAR99 controlled data.

PPG Aerospace
Sealants and Coatings
Darlington Road
Shildon, Co Durham UK
DL4 2QP

www.ppgaerospace.com

Issue Date: 06/22

Lit: 4309