

09W015 White High Build Sanding Surfacers

TECHNICAL DATA SHEET

Product Description

09W015 is a chrome free, chemically cured, chemical and solvent resistant polyurethane high build sanding surfacer. 09W015 is designed to fill in the irregularities and surface defects commonly experienced on aluminum, fiber glass, and composite surfaces.

- Resistant to hydraulic fluids, lubricating oils, diesel fuel, and water
- Quick recoat time
- Fast dry with addition of accelerator or low temperature oven cure
- Excellent flow and leveling
- Easily sanded
- Can be applied with brush or roller

Components



Mix ratio (by volume):

- | | |
|----------------------------------|------------|
| • 09W015 (base component) | 6 parts |
| • 36X194CAT (catalyst component) | 1 part |
| • CA1805CX (thinner component) | 0.25 parts |

Note: Addition of CA1805CX thinner component may be adjusted to achieve desired application viscosity.

Specifications



09W015 meets the performance requirements of:

- BAMS 565-015

Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.

Product Compatibility:

09W015 is compatible with the following primer specifications:

- BAMS 565-008

09W015 is compatible with the following topcoat specifications:

- BAMS 565-009

09W015 White High Build Sanding Surfer

Surface Preparation and Pretreatments



09W015 primer can be applied over clean, dry, intact primed aluminum and unprimed composite surfaces. Aluminum surfaces need to be primed with a urethane compatible coating. For further information, refer to the above mentioned primers.

Instructions for Use



Mixing Instructions:

Stir or shake 09W015 base component for 5 to 10 minutes to ensure any pigment, which may have settled on the bottom of the can, has been fully incorporated into the base. Slowly add six (6) volumes of 09W015 base component to one (1) volume of 36X194CAT catalyst component and mix thoroughly. Add one quarter (0.25) volumes of CA1805CX thinner component and mix thoroughly to uniformity. Mix ratio with 36X194CAT is 6 parts base: 1 part activator: 0.25 parts thinner.

Note: It is important to condition the paint for 24 hours prior to mixing by placing all materials in the shop or hangar, with ambient temperatures between 15° and 30°C (59° to 86°F). The minimum temperature of the paint components should be 15°C (59°F) prior to mixing.




Induction Time:

Not Applicable



Viscosity: (23°C/73°F)

- #4 Ford cup 14 to 21 seconds



Pot Life:

3 - 4 hours @ 20 - 26°C (68 - 78°F)

09W015 White High Build Sanding Surfacers

Application Guidelines

Recommended Application Conditions:

Temperature	15 - 30°C (59 - 86°F)
Relative Humidity	20 - 90%

Application:

Ground the aircraft and the application equipment before spraying. Stir the surfacer slowly during the application. The suggested film thickness is 25 to 150 microns (1 to 6 mils) before sanding. This can be accomplished by two or three medium coats with a 50% overlap. Note the initial coat should be allowed to tack up before applying the next coat. When using three coat process, allow the second coat to tack up before applying the third coat. Applying a new coat before the existing one has tacked up may result in sagging and possibly pinholes.


These application guidelines represent PPG's best advice in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.



Theoretical coverage:

17.5 square meters/liter at 25 microns dry film (720 square feet/gallon at 1 mil dry film)

Recommended dry film thickness; 25 to 150 microns (1 to 6 mils)



Dry Film Density:

1.84 grams/cubic centimeter (15.4 lbs./gallon)

Dry Film Weight:

4.36 grams/square meter at 25 microns dry film (0.0096 lbs./square feet at 1 mil dry film)

09W015 White High Build Sanding Surfacers



Equipment:

09W015 is compatible with the spray equipment listed below:

Equipment Type	Tip Size	Pot Pressure	Atomization Pressure at the Cap
Electrostatic Air Spray Gun	1.2 mm	10 to 20 psi (0.69 to 1.4 bar)	45 to 60 psi (3.1 to 4.1 bar)
High Volume Low Pressure Spray Gun (HVLPP)	1.3 - 1.8 mm	10 to 20 psi (0.69 to 1.4 bar)	10 psi maximum (0.69 bar)

Equipment Cleaning:

Clean spray equipment as soon as possible after use. Flush spray equipment with DeSoto® CN20, DeSoto® CN44, or Desoclean™ 45 high performance solvent cleaner.

Physical Properties (product)



Color White



Gloss <20 G.U. at 60°



Dry Times at 18 - 24°C (65 - 75°F) 50% ± 10% RH

Tack Free	2 hours
Recoat Time with itself	1 - 12 hour
Dry Hard	4 hours
Dry to Sand	12 hours minimum
Overcoat Time after sanding	1 - 24 hours

Force dry schedule for Dry to Sand:

Allow a minimum of 15 minutes flash off time at ambient conditions (70° ± 5°F and 50% ± 10% relative humidity) prior to exposing painted parts to high temperatures. Complete testing should be done prior to use. Below are suggested starting points. Other variables may affect cure schedules.

09W015 White High Build Sanding Surfacers

Temperature	Dry to Sand
71°C (120°F)	6 hours minimum

Note: These guidelines for the heat-accelerated cure of two component urethane coatings. These parameters are to achieve dry sand time. Your actual results may depend on the mass of the parts or degree of cure needed.

VOC

VOC:

Mixed, ready to use VOC (EPA method 24)	40 grams/liter
Base Component	45 grams/liter
Catalyst Component	0 grams/liter
Thinner Component	0 grams/liter



Flash Point closed cup:

Base Component	-20°C (-4°F)
Catalyst Component	-20°C (-4°F)
Thinner Component	-9°C (15°F)

Shelf Life:

12 months from date of manufacture to most OEM material specifications. Consult the specification to verify shelf life requirements.

24 months from date of manufacture for PRC-DeSoto Standard.

Note: Shelf life is provided for original, unopened containers.

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 13°C to 32°C (55°F to 90°F) to ensure shelf life.

Note: When procuring to a qualified material specification, follow those storage instructions.

09W015 White High Build Sanding Surfacers

Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

Additional information can be found at: www.ppgaerospace.com

For sales and ordering information call the local PPG office at the numbers listed below:

Asia Pacific

ASC – Australia

Tel 61 (3) 9335 1557

Fax 61 (3) 9335 3490

ASC – Japan

Tel 81 561 35 5200

Fax 81 561 35 5201

ASC – South East Asia

Tel 65 6861 1119

Fax 65 6861 6162

ASC – Suzhou

Tel (86-512) 6661 5858

Fax (86-512) 6661 6868

ASC – Tianjin

Tel (86-022) 2482 8625

Fax (86-022) 2482 8600

Americas

1 (818) 362-6711 or 1-800-AEROMIX

Europe and Middle East

ASC – Central Europe

Tel 49 (40) 742 193 10

Fax 49 (40) 742 139 69

ASC – Middle East & India

Tel (971) 4 883 9666

Fax (971) 4 883 9665

ASC – North Europe

Tel 44 (0) 1388 770222

Fax 44 (0) 1388 770288

ASC – South Europe

Tel 33 (0) 235 53 43 71

Fax 33 (0) 235 53 54 44

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PRC-DeSoto International,
Inc.

12780 San Fernando Road
Sylmar, CA 91342

www.ppgaerospace.com

Issue Date: 10/16

Lit: 4396