

### N58479/T508 Polyester Filler

#### Product Description

N58479/T508 is a two component polyester based filler for direct application to metal and composite substrates, for filling of holes and surface imperfections.

- High viscosity
- Excellent sandability
- Ambient curing
- Long pot life enables filling of large areas using a single mix

#### Components



##### Mix Ratio (by weight)

- |                         |           |
|-------------------------|-----------|
| • N58479 (Base)         | 100 parts |
| • N59029NV-3 (Hardener) | 1.5 part  |

#### Specifications



N58479/T508 is qualified to the following specifications:

- DAN 1090
- ECS 2202
- MEP 10-066

*Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.*

#### Surface Preparation and Pretreatment



Ensure surface is clean, dry and intact, using a high performance cleaner, DeSoto® CN20 or Desoclean™ 45 solvent cleaners are recommended. Maximum adhesion is achieved on well abraded surfaces such as metal, wood and glass fibre reinforced polyester.

## N58479/T508

# N58479/T508 Polyester Filler

## Instructions for Use



Before adding the hardener to the base, thoroughly stir or shake the base component until a smooth uniform mix is obtained. Immediately after adding the hardener to the base, stir thoroughly until uniform.

*Note: All products and components should be placed in ambient conditions of 15-30°C (59-86°F) for at least 24 hours prior to mixing and application.*




### **Induction Time:**

Not applicable



### **Viscosity:** (23°C/73°F)

Not applicable - Product supplied in the form of a paste



### **Pot Life:**

30 minutes maximum @ 23±2°C (70-77°F)

## Application Guidelines

### **Recommended Application Conditions:**

Temperature	15-35°C (59-95°F)
Relative Humidity	30-85%

### **Application:**

Apply as required using a filler knife or spatula




### **Theoretical Coverage:** (ready for use)

8 m<sup>2</sup>/Lt @ 100µm dry film thickness  
320 ft<sup>2</sup>/US gal @ 4 mil dry film thickness

### **Recommended Dry Film Thickness:**

Up to 100µm  
4 mil



### **Dry Film Density:**

1.8g/cm<sup>3</sup>  
15lbs/US gal

# N58479/T508 Polyester Filler

## Dry Film Weight:

210 g/m<sup>2</sup> @ 100 µm dry film thickness

8400 lbs/ft<sup>2</sup> @ 4 mil dry film thickness

*Note: These application guidelines represent PPG's best advice for usage in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.*

## Equipment:



Applicable using a filler knife or plastic/rubber spatula

## Physical Properties



### Colour:

White




### Gloss:

Not applicable



Drying Times	23°C (73°F)
Dry to Sand	1.5 to 2 hours
Dry to Overcoat	2 to 3 hours

*Note: Drying times listed above are dependent upon film thickness applied, air flow conditions and application technique.*



### Flash Off Time:

Not applicable



### VOC: (ASTM)

Mixed ready for use

<250 g/Lt



### Flash Point:

N58479 Base Component  
N59029NV-3 Hardener

31°C (88°F)  
Not Applicable

# N58479/T508 Polyester Filler

## Shelf Life:

N58479

9 months in original unopened container

N59029NV-3 Hardener

9 months in original unopened container

*Note: Shelf life may vary due to OEM specification requirements. Refer to container label for specific shelf life information.*

*Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.*

## Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

*Note: When procuring to a qualified material specification, follow those storage instructions.*

# N58479/T508 Polyester Filler

## Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

**For industrial use only. Keep away from children.**

**Additional information can be found at: [www.ppgaerospace.com](http://www.ppgaerospace.com)**

**For sales and ordering information call the local PPG office at the numbers listed below:**

### **Asia Pacific**

**ASC – Australia**  
Tel 61 (3) 9335 1557  
Fax 61 (3) 9335 3490

**ASC – Japan**  
Tel 81 561 35 5200  
Fax 81 561 35 5201

**ASC – South East Asia**  
Tel 65 6861 1119  
Fax 65 6861 6162

**ASC – Suzhou**  
Tel (86-512) 6661 5858  
Fax (86-512) 6661 6868

**ASC – Tianjin**  
Tel (86-022) 2482 8625  
Fax (86-022) 2482 8600

### **Europe and Middle East**

**ASC – Central Europe**  
Tel 49 (40) 742 193 10  
Fax 49 (40) 742 139 69

**ASC – Middle East & India**  
Tel (971) 4 883 9666  
Fax (971) 4 883 9665

**ASC – North Europe**  
Tel 44 (0) 1388 770222  
Fax 44 (0) 1388 770288

**ASC - South Europe**  
Tel 33 (0) 235 53 43 71  
Fax 33 (0) 235 53 54 44

### **Americas**

1 (818) 362-6711 or 1-800-AEROMIX

**Desoclean, Desothane, Desoprime and DeSoto are trademarks of PRC-DeSoto International, Inc.**

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

*This document has been reviewed by the PPG Aerospace Export Control Department and has been determined to contain only EAR99 controlled data.*

PPG Aerospace  
Sealants and Coatings  
Darlington Road  
Shildon, Co Durham UK  
DL4 2QP

[www.ppgaerospace.com](http://www.ppgaerospace.com)

Issue Date: 11/24  
Lit: 4314