

# ZR-6375 Temporary Protective Coating

## TECHNICAL DATA SHEET

### Product Description

ZR-6375 is a chrome-free, water-based coating formulated for the temporary protection of aluminum surfaces during manufacturing operations such as roll forming, stretch bending, drop-hammer and riveting operations. It provides a tough, abrasion-resistant, transparent film, thus permitting any layout work that may be necessary. ZR-6375 can be removed with BMS 15-12 Type II approved removers or SC-1101S. The service life of ZR-6375 is 8 months for outdoor or indoor storage

- Chrome-free
- Water-based
- Non-flammable in liquid form
- Transparent-light green
- Compatible with standard type spray guns - either air or airless
- 8 month service life for outdoor or indoor storage

### Components



#### Mix ratio (by volume):

- ZR-6375

Single component, ready to use product

### Specifications



ZR-6375 is qualified to the following specification:

- BMS 15-12 Type I Class 1

*Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.*

### Surface Preparation and Pretreatments



Apply to dirt and oil free surfaces.

# ZR-6375 Temporary Protective Coating

## Instructions for Use



### Mixing Instructions:

ZR-6375 is ready to use with no additional components. Check to ensure that no freezing has occurred in shipping or during storage period. Upon opening container, manually stir thoroughly to overcome any settling. Avoid shaking as product can foam when agitated. No thinning of the compound is required prior to application. The compound should not be admixed with or allowed to come in contact with solvents at any time, since this will cause coagulation. If, for any reason, thinning is desired, only water should be used. Spray equipment can be cleaned with water.




### Induction Time:

Not Required



### Viscosity: (23°C/73°F)

- Krebs Units 68 - 103



### Pot Life:

Not Applicable

## Application Guidelines

### Recommended Application Conditions:

Temperature	18 - 30°C (65 - 86°F)
Relative Humidity	20 - 90%

### Application:

A dry film of one mil in thickness is recommended. This is achieved by applying a wet film of three mils in one coat. Good spray techniques should be used in the application of ZR-6375. With an atomizing air system, a DeVilbiss MBC gun with an FF nozzle and #765 air cap or equivalent is recommended. Just sufficient pressure on the material should be used to deliver the compound to the gun. Atomizing air pressure of 70 lbs. per square inch minimum is desired. If airless spray is to be used, a Graco President Model 28:1 pump utilizing a Reflex gun with a #163-409 spray tip is recommended.

## ZR-6375 Temporary Protective Coating

### Removability:

ZR-6375 is removed by applying a wet film of up to 20 mils thick of the SC-1101S remover. It should be allowed to soak into the ZR-6320 for approximately 5 to 20 minutes and then flushed off with water under pressure accompanied by mild brushing.

For spot removal, such as in areas to be riveted, toluene or denatured ethyl alcohol will readily dissolve a one mil coating of ZR-6375. (Heavier films of ZR-6320 are not necessary, and are more difficult to remove.) Apply the solvent with a cloth, allow a few seconds for penetration, and then wipe the area with a clean solvent-wet cloth.

*These application guidelines represent PPG's best advice for usage in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.*



### Theoretical Coverage:

43 square meters/liter at 25 microns dry film (463 square feet/gallon at 1 mil dry film)  
Recommended dry film thickness; 25 microns (1 mil)



### Equipment:

ZR-6375 is compatible with most forms of spray equipment. See application section for details.

### Equipment Cleaning:

Flush spray equipment ONLY with water.

## Physical Properties (product)



**Color:** Transparent green



**Gloss:** Not Applicable

**Percent Solids:** 33 ± 2 %

## ZR-6375 Temporary Protective Coating



<b>Dry Times</b>	<b>22 - 28°C (71 - 84°F)</b>
Tack Free	20 minutes
Full Hardness	24 hours

Drying can be accelerated by warm air.

### VOC

#### VOC (EPA method 24):

ZR-6375 <135 grams/liter

#### Physical Constants:

Weight/gallon: 8.6 ± 0.2 pounds/gallon



#### Flash point closed cup:

ZR-6375 93°C (>200°F)

#### Shelf Life:

BMS 15-12: 6 months from date of manufacture.

*Note: Shelf life is provided for original, unopened containers.*

*Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.*

### Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 13°C to 32°C (55°F to 90°F) to ensure shelf life. This is a water-base compound and should be protected from freezing. Never allow this product to freeze. Once frozen, application and protective properties are unstable and not warranted.

*Note: When procuring to a qualified material specification, follow those storage instructions.*

# ZR-6375 Temporary Protective Coating

## Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

**For industrial use only. Keep away from children.**

**Additional information can be found at: [www.ppgaerospace.com](http://www.ppgaerospace.com)**

**For sales and ordering information call the local PPG office at the numbers listed below:**

### **Asia Pacific**

#### **ASC – Australia**

Tel 61 (3) 9335 1557  
Fax 61 (3) 9335 3490

#### **ASC – Japan**

Tel 81 561 35 5200  
Fax 81 561 35 5201

#### **ASC – South East Asia**

Tel 65 6861 1119  
Fax 65 6861 6162

#### **ASC – Suzhou**

Tel (86-512) 6661 5858  
Fax (86-512) 6661 6868

#### **ASC – Tianjin**

Tel (86-022) 2482 8625  
Fax (86-022) 2482 8600

### **Americas**

1 (818) 362-6711 or 1-800-AEROMIX

### **Europe and Middle East**

#### **ASC – Central Europe**

Tel 49 (40) 742 193 10  
Fax 49 (40) 742 139 69

#### **ASC – Middle East & India**

Tel (971) 4 883 9666  
Fax (971) 4 883 9665

#### **ASC – North Europe**

Tel 44 (0) 1388 770222  
Fax 44 (0) 1388 770288

#### **ASC – South Europe**

Tel 33 (0) 235 53 43 71  
Fax 33 (0) 235 53 54 44

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PRC-DeSoto International, Inc.  
12780 San Fernando Road  
Sylmar, CA 91342  
[www.ppgaerospace.com](http://www.ppgaerospace.com)

Issue Date: 07/16  
Lit: 4426