


PAC33CF Polyurethane Primer

Product Description

PAC33CF is a two component, corrosion inhibitive, polyurethane primer modified with epoxy resin. PAC33CF is designed for use with aerospace paint systems.

- Chromate free
- Excellent corrosion resistance
- Designed for ambient curing
- High chemical resistance and flexibility
- Designed for use over P99 wash primer
- Compatible over pre-treated alloy for interior and exterior parts

Components



Mix Ratio (by volume)

- 4360/... (Base) 5 parts
- 0736/9000 (Activator) 1 part
- 0433/9000 (Thinner) 4-5 parts

Specifications



PAC33CF is qualified to:

- AMS 3095

When used over wash primer P99, PAC33CF meets the performance requirements of:

- AIMS 04-04-012
- AIMS 04-04-013

Product Compatibility

PAC33CF is compatible with the following:

- Sulfo-chromic or anodized pre-treated aluminum
- P99 etch primer to AIMS 04-04-012
- Polyurethane topcoat to AIMS 04-04-003 & AIMS 04-04-012

Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.

PAC33CF Polyurethane Primer

Surface Preparation and Pretreatment



Ensure that the correct surface pre-treatment has been carried out, and that drying and overcoat times are observed. Ensure the surface is clean, dry and intact using high performance solvent cleaner. DeSoto® CN20 or Desoclean™ 45 solvent cleaners are recommended.

Instructions for Use



Ensure all mixing and measuring containers are clean and free from contamination. Hand stir or mechanically agitate base material until all components are uniformly dispersed. Add activator to base, mix thoroughly and thin to recommended viscosity using approx. 4-5 volumes of thinner.

Note: All products and components should be placed in ambient conditions of 15-30°C (59-86°F) for at least 24 hours prior to mixing and application.



Induction Time:


Not required



Viscosity: (21°- 25C/70 - 77°F)

- | | |
|------------|---------------|
| • AFNOR2.5 | 45-55 seconds |
| • AFNOR4 | 14-16 seconds |
| • BSB3 | 26-29 seconds |
| • BSB4 | 14-17 seconds |
| • FORD4 | 12-15 seconds |
| • ISO3 | 29-50 seconds |
| • ISO4 | 15-22 seconds |
| • ZAHN2 | 15-19 seconds |

Note: Viscosities quoted are typical ranges obtained when using specified mix ratio.



Pot Life:

8 hours @ 21-25°C (70-77°F)

Application Guidelines

Recommended Application Conditions:

Temperature 15 - 35°C (59 - 95°F)
Relative Humidity 35 - 70%

PAC33CF Polyurethane Primer

Application:

Apply 1 cross coat or one wet coat with 50% overlap to achieve recommended dry film thickness of 15-25 μm . Avoid applying higher film thicknesses as this can create orange peel and intercoat adhesion failures.




Theoretical Coverage: (ready for use)

8-9 m^2 Lt @ 20 μm dry film thickness
320-360 ft^2 US gal @ 0.8 mil dry film thickness

Recommended Dry Film Thickness:

15 - 25 μm
0.6 - 1 mil



Dry Film Density:

1.84 g/cm^3
15.36 $\text{lbs}/\text{US gal}$

Dry Film Weight:

37 g/m^2 @ 20 μm dry film thickness
0.007 lbs/ft^2 @ 0.8 mil dry film thickness

Note: These application guidelines represent PPG's best advice for usage in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.

Equipment: PAC33CF is compatible with most current types of spray equipment.



Equipment	Tip Size	Flow Rate	Air Pressure
Airmix Kremlin	$\varnothing = 0.28\text{mm}$ - Angle 60° Ref: 06.134	320 to 360 ml/min	725 to 870 psi (50 to 60 bar)
HVLP	1.2 mm		22 to 29 psi (1.5 to 2 bar)
Conventional Air Spray	1.5 mm		43 to 58 psi (3 to 4 bar)
Airless	Not Recommended		
Airless Air-assisted	609 to 611	360 to 400 ml/min	58 to 73 psi (4 to 5 bar)
PRO 3500 or Pro XS4	1.2 to 1.5 mm	360 to 400 ml/min	72 to 87 psi (5 to 6 bar)

Equipment Cleaning:

Clean spray equipment before use and as soon as possible after use. DeSoto® CN20, CN44 or Desoclean™ 45 solvent cleaners are recommended.

PAC33CF Polyurethane Primer

Physical Properties

**Colour:**

Beige (4360/3031)

Grey (4360/2015)


**Gloss:**

Not Applicable



Drying Times @ 50 % R.H.	23°C (73°F)	100°C (212°F)
Dust Free	30 mins	
Dry to Handle	1 hour	
Dry to Mask	2 hours	20 minutes
Dry to Sand	2 hours	
Dry to Overcoat	1 hour (min.) 72 hours (max.)	
Dry to Fly	48 hours min.	
Full Cure	7 days	

Note: Drying times listed above are dependent upon film thickness applied, air flow conditions and application technique.

**Flash Off Time:**

20 minutes at 23°C (73°F) prior to accelerated cure.

**VOC: (ASTM)**

Mixed ready for use	735 g/Lt
4360/... Base Component	690 g/Lt
0736/9000 Activator	390 g/Lt
0433/9000 Thinner	880 g/Lt

**Flash Point:**

4360/... Base Component	3°C (37°F)
0736/9000 Activator	50°C (122°F)
0433/9000 Thinner	4°C (39°F)

Shelf Life:

4360/... Base Component	24 months in original unopened container
0736/9000 Activator	24 months in original unopened container
0433/9000 Thinner	10 years in original unopened container

PAC33CF Polyurethane Primer

Note: Shelf life may vary due to OEM specification requirements. Refer to container label for specific shelf life information.

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

Note: When procuring to a qualified material specification, follow those storage instructions.

PAC33CF Polyurethane Primer

Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

Additional information can be found at: www.ppgaerospace.com

For sales and ordering information call the local PPG office at the numbers listed below:

Asia Pacific

ASC – Australia
Tel 61 (3) 9335 1557
Fax 61 (3) 9335 3490

ASC – Japan
Tel 81 561 35 5200
Fax 81 561 35 5201

ASC – South East Asia
Tel 65 6861 1119
Fax 65 6861 6162

ASC – Suzhou
Tel (86-512) 6661 5858
Fax (86-512) 6661 6868

ASC – Tianjin
Tel (86-022) 2482 8625
Fax (86-022) 2482 8600

Europe and Middle East

ASC – Central Europe
Tel 49 (40) 742 193 10
Fax 49 (40) 742 139 69

ASC – Middle East & India
Tel (971) 4 883 9666
Fax (971) 4 883 9665

ASC – North Europe
Tel 44 (0) 1388 770222
Fax 44 (0) 1388 770288

ASC - South Europe
Tel 33 (0) 235 53 43 71
Fax 33 (0) 235 53 54 44

Americas

1 (818) 362-6711 or 1-800-AEROMIX

Desoclean and DeSoto are trademarks of PRC-DeSoto International, Inc.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PPG Aerospace
Sealants and Coatings
Darlington Road
Shildon, Co Durham UK
DL4 2QP
www.ppgaerospace.com

Issue Date: 06/19
Lit: 4249