

Z-6160 Peelable Preservation Basecoat

Product description

Z-6160 is a sprayable, peelable preservation coating formulated for protection of plastic, metal, porcelain and painted surfaces during in-plant fabrication, operation, shipping and storage.

- Chrome-free
- Corrosion resistant
- Water-borne
- Nonflammable in liquid form
- Low heavy metals content
- Suitable for use on nuclear equipment
- 12 month service life for indoor or outdoor storage

Z-6160 can be used alone or for added exterior durability it can be overcoated with Z-6148 preservation topcoat.

Components



Mix ratio (by volume):

- Z-6160

Single component, ready to use coating

Specifications



Z-6160 meets the following specification:

- MIL-PRF-6799 Type II Class 1A

Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.

Surface preparation and pretreatments



Apply to oil and dirt free substrates.

Instructions for use



Mixing Instructions:

Z-6160 is ready to use with no additional components. Check to ensure that no freezing has occurred during shipping or storage period. Upon opening container, manually stir thoroughly to overcome any settling. If using a mechanical paint shaker, the recommended mix time is 5 minutes.


Z-6160 Peelable Preservation Basecoat

**Induction time:**

Not Required

**Viscosity:** (23°C/73°F)

12,000 to 25,000

**Pot life:**

Not Applicable

Application guidelines

Recommended application conditions:

Temperature	15 – 30°C (59 – 86°F)
Relative Humidity	20 – 90%

Application:

When applying over lacquered surfaces ensure that the lacquer film is fully dry. When used over enamel, urethane or epoxies, ensure that these are fully cured per the manufacturer's recommendations, before using Z-6160. For equipment which will be stored indoors, be sure to apply a minimum film thickness of 4 mils (.004"). A .004" film can be applied to a vertical surface in one coat. On equipment to be stored for many months exposed to rain, sun and snow, we recommend that an 8 mil (.008") film be applied in two coats, drying one hour between coats. After the film has dried enough to lose its gloss, it should then be overcoated with Z-6148 preservation topcoat to a thickness of 2 mils (.002").

These application guidelines represent PPG's best advice for usage in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.

**Theoretical coverage:**

55.8 square meters/liter at 25 microns dry film (600 square feet/gallon at 1 mil dry film)

Recommended dry film thickness for indoor storage; 100 microns (4 mils)

Recommended dry film thickness for outdoor storage; 200 microns (8 mil)

Z-6160 Peelable Preservation Basecoat



Equipment:

Z-6160 is compatible with the following spray equipment

Equipment type	Tip size	Pressure	Atomization pressure at the cap
Air Assisted Airless Spray Gun	#613 to #615 (Graco Nomenclature)	Pump pressure 700 to 1200 psi (48 to 82 bar)	40 to 60 psi (2.8 to 4.1 bar)
High Volume Low Pressure Spray Gun (HVLP)	1.5 mm to 1.8 mm	10 to 20 psi (0.69 to 1.4 bar)	10 psi maximum (0.69 bar)
Conventional Air Spray Gun	1.5 mm to 1.8 mm	10 to 20 psi (0.69 to 1.4 bar)	45 to 60 psi (3.1 to 4.1 bar)

Equipment Cleaning:

Flush spray equipment ONLY with water.

Physical properties (product)



Color: Black



Gloss: Not Applicable

Elongation: 200%

Non-volatiles: 37.5% minimum

Tensile strength: 2900 psi minimum

Z-6160 Peelable Preservation Basecoat



Dry Times		22 - 28°C (71 - 84°F)
Time between coats		1 hour
Full cure		16 hours
Overcoat time with Z-6148 if applicable		After last coat of Z-6160 has lost its gloss the Z-6148 can be applied. The system will dry together, achieving full cure in 16 hours

Drying can be accelerated by circulation of warm air.

Note: For indoor storage only one coat is required, for outdoor storage two coats are recommended.



VOC (EPA method 24):

Z-6160 <12 grams/liter

Physical constants:

Weight/gallon 8.6 ± 0.2 pounds/gallon



Flash point closed cup:

Z-6160 >93.3°C (200°F)

Shelf life:

12 months from date of manufacture.

Note: Shelf life is provided for original, unopened containers.

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 13°C to 32°C (55°F to 90°F) to ensure shelf life. Never allow this product to freeze. Once frozen, application and protective properties are unstable and not warranted.

Z-6160 Peelable Preservation Basecoat

Note: When procuring to a qualified material specification, follow those storage instructions.

Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

Additional information can be found at: www.ppgaerospace.com

For sales and ordering information call the local PPG office at the numbers listed below:

Asia Pacific

ASC – Australia
Tel 61 (3) 9335 1557
Fax 61 (3) 9335 3490

ASC – Japan
Tel 81 561 35 5200
Fax 81 561 35 5201

ASC – South East Asia
Tel 65 6861 1119
Fax 65 6861 6162

ASC – Suzhou
Tel (86-512) 6661 5858
Fax (86-512) 6661 6868

ASC – Tianjin
Tel (86-022) 2482 8625
Fax (86-022) 2482 8600

Americas

1 (818) 362-6711 or 1-800-AEROMIX

Europe and Middle East

ASC – Central Europe
Tel 49 (40) 742 193 10
Fax 49 (40) 742 139 69

ASC – Middle East & India
Tel (971) 4 883 9666
Fax (971) 4 883 9665

ASC – North Europe
Tel 44 (0) 1388 770222
Fax 44 (0) 1388 770288

ASC – South Europe
Tel 33 (0) 235 53 43 71
Fax 33 (0) 235 53 54 44

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PRC-DeSoto International, Inc.
12780 San Fernando Road
Sylmar, CA 91342
www.ppgaerospace.com

Issue Date: 12/19
Lit: 4491